

English Version (Japanese Translation)

[screen ink](#)[additive](#)[For other inks](#)

Additive Applications Promoting scleroticability | solvent-based

JA-980 Hardening Agent

Block isocyanate resin.

A hardener specifically designed for heat curing.

High-temperature curing type.

Product Features

- There is no pot life (usable time) after addition.
- Non-yellowing type with good weather resistance.

Features

[hardness](#)

Endurance

[Physical Endurance](#)[weather resistance](#)

Specifications

Lotus form	Characteristics
100g metal cans	mucus

How to use

- The dosage is 5~15 parts per 100 parts of ink.

Curing Method & Conditions

Evaporative Drying Conditions

hardening drying

Above 150° C, 30 minutes

Notes

- For safety precautions when using the product, please refer to the product's Safety Data Sheet (SDS).
- The contents provided in this information may be changed or revised without prior notice.
- When using the device, please thoroughly consider the conditions based on the evaluation results of the equipment and substrate actually being used.